

**DOLPHIN 7035 SERIES**

**MidVisc WinSeal™ ADHESIVE/SEALANTS**

**DESCRIPTION:** These strong, fast drying, thermoplastic rubber adhesive/sealants are formulated with controlled flow viscosity; the rheology balance of these products allow them to self level without running on vertical surfaces. Their low viscosity permits them to flow into seams and self-level; their thixotropy prevents flowing out of the seams and resists flow on vertical surfaces. Ease of application from pump oilers to narrow seams permits their use as trim sealants around windows and along corner and edge trim; they may also be used to seal the mechanical fasteners used in the assembly of radius windows.

These adhesive/sealants adhere to most surfaces including glass, fiberglass, steel, aluminum, rubber and most primed and painted surfaces. Because of their excellent exterior durability, the **DOLPHIN 7035 Series** of adhesive/sealants offer the ultimate in flexibility, even when exposed to extremely low temperatures. These products may be painted over, if necessary; paint adheres well and these adhesive/sealants will not discolor most finishes.

**APPLICATION:** These products are normally supplied in ones, fives and drums. Because solvent evaporation will increase the viscosity of these adhesive/sealants, it is recommended that they be pumped from closed containers; the **DOLPHIN 7035 Series** may be dispensed from pump oilers. These adhesive/sealants skin over quickly after application; they may be painted over as soon as a skin forms. Thin with toluene, if necessary; equipment may be cleaned with toluene or xylene after use.

**PROPERTIES:**

Color:	<b>DOLPHIN 7035</b> - Black <b>DOLPHIN 7036</b> - Aluminum <b>DOLPHIN 7038</b> - White
Solids by wt:	56% - 62%
Specific Gravity:	1.02 – 1.11

Technical Data Sheets are intended as a guide for our customers and are based on tests believed reliable. Since usage of our products is beyond our control, we can make no warranty, expressed or implied, as to such use, or related activities, whether or not in accordance with directions. Our statements shall not be construed as inducements to infringe any patent.

**DOLPHIN 7035 Series**

Flash Point, Seta Flash CC: ASTM D 3278	40° - 50° F
Dry Time @ 68° F; 50% RH ASTM D 1640; .125" thick	5 minutes set to touch 24 hours through dry

**THE FOLLOWING TESTS WERE PERFORMED AFTER  
DRYING 21 DAYS @ 68° F (20° C); 50% RH**

Tensile Strength: ASTM D 412; Die C; Pulled @ 5 in./min.	350 psi
Elongation: ASTM D 412; Die C; Pulled @ 5 in./min.	1000%
Low Temperature Flexibility: ASTM C 711; 2.5" mandrel @ -20° F (-29° C)	No cracking No loss of adhesion
Effects of Heat Aging: ASTM C 792; 336 hours @ 158° F (70° C)	Flexibility maintained No loss of adhesion
QUV Light/Water Exposure: ASTM G 53; QUV-A 340 lamps 1344 hours	No cracking No discoloration No adhesion loss

LOS033106

Technical Data Sheets are intended as a guide for our customers and are based on tests believed reliable. Since usage of our products is beyond our control, we can make no warranty, expressed or implied, as to such use, or related activities, whether or not in accordance with directions. Our statements shall not be construed as inducements to infringe any patent.